## (19) 世界知的所有権機関 国際事務局



## A CORDA BURNINDO DE ROCORDO CORDO RANDA BURNO DA AN CONTRA DOMA CORDA BARAN ENGLA PARA CORDA PARA CORDA PARA CO

(43) 国際公開日 2005年4月28日(28.04.2005)

PCT

## (10) 国際公開番号 WO 2005/037449 A1

(51) 国際特許分類<sup>7</sup>: B05D 1/36, 5/06, 7/24, C09D 201/02

(21) 国際出願番号:

PCT/JP2004/015510

(22) 国際出願日:

2004年10月20日(20.10.2004)

(25) 国際出願の言語:

日本語

(26) 国際公開の言語:

日本語

(30) 優先権データ: 特願 2003-360200

л 2003年10月21日(21.10.2003)

- (71) 出願人(米国を除く全ての指定国について): 関西ペイ ント株式会社 (KANSAI PAINT CO., LTD.) [JP/JP]; 〒 6618555 兵庫県尼崎市神崎町 3 3番 1 号 Hyogo (JP).
- (72) 発明者; および
- (75) 発明者/出願人 (米国についてのみ): 藤枝 宗 (FU-JIEDA, Tsukasa) [JP/JP]; 〒2220032 神奈川県横浜市 港北区大豆戸町355-21 Kanagawa (JP).
- (74) 代理人: 三枝 英二 , 外(SAEGUSA, Eijl et al.); 〒 5410045 大阪府大阪市中央区道修町 1-7-1 北浜 TNKビル Osaka (JP).

- (81) 指定国(表示のない限り、全ての種類の国内保護が 可能): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR. BW, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) 指定国(表示のない限り、全ての種類の広域保護が可 能): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), ユーラシア (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), ヨーロッパ (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).

添付公開書類: 国際調査報告書

2文字コード及び他の略語については、 定期発行される 各PCTガゼットの巻頭に掲載されている「コードと略語 のガイダンスノート」を参照。

(54) Title: METHOD FOR FORMING BRIGHT COATING FILM

(54) 発明の名称: 光輝性塗膜形成方法

(57) Abstract: A method (I) for forming a bright coating film, which comprises a process (1) of applying, on an article to be applied, an aqueous bright thermosetting base coating (A) in two to five stages, wherein the application is carried out in such a manner that each coating film in the second stage or a later stage has a thickness of 0.3 to 5  $\mu$ m in terms of a cured film, a process (2) of applying a thermosetting clear coating (B) on an uncured or thermally cured coating film of the base coating (A), a process (3) of applying an aqueous bright thermosetting base coating (C) in two to five stages on an uncured or thermally cured coating film of the thermosetting clear coating (B), (4) a process of applying a thermosetting clear coating (D) on an uncured or thermally cured coating film of the base coating (C), and a process (5) of heating a four layer coating film comprising a coating film of the base coating (A), a coating film of the clear coating (B), a coating film of the base coating (C) and a coating film of the clear coating (D), to form a cured product of said four layer coating film; and a method (II) according to the method (I) for forming a bright coating film, which further includes a step of applying a thermosetting clear coating (E) followed by curing.

(57)要約: 本発明は、(i)被塗物上に、水性光輝性熱硬化型ペース塗料(A)を2乃至5ステージで塗装する工程で あって、第2ステージ以降の各ステージにおける塗装膜厚が、硬化膜厚で、Ο. 3~5μmとなるように塗装する 工程、(2)ペース塗料 (A) の未硬化又は加熱硬化した塗膜上に、熱硬化型クリヤー塗料 (B) を塗装する工程、(3) クリヤー塗料 (B) の未硬化又は加熱硬化した塗膜上に、水性光輝性熱硬化型ペース塗料 (C) を2乃至5ステ ○ ジで塗装する工程、(4)ペース塗料 (C) の未硬化又は加熱硬化した塗膜上に、熱硬化型クリヤー塗料 (D) を塗装 する工程、及び(5)ペース塗料(A)の塗膜、クリヤー塗料(B)の塗膜、ペース塗料(C)の塗膜及びクリヤー塗 料(D)の塗膜からなる四層塗膜を、加熱して、硬化した該四層塗膜を得る工程を含む光輝性塗膜形成方法1、並 びに 方法 I において、更に熱硬化型クリヤー塗料(E)を塗装、硬化する光輝性塗膜形成方法IIを提供する。

